



Product Data Sheet

Product name	23FT10		
		Value	Unit
Reinforcement	Fiber(s)	Flax twill fiber fabric	
	Fiber orientation	0°/ 90°	
	Carbon Fabric FAW	200	g/m ²
Resin	PCR PC		
Laminate	Specific gravity	1.31	g/cc
	Fiber content by volume	45.3	%
	Fiber content by weight	50	%
	Thickness	0.9 ±0.1	mm
	Area weight	1200	g/m ²
Appearance	Color	Nature	
	Construction	Twill	
Process	Mold temperature	160 to 230	°C
Recommendation	Forming pressure	10 to 30	Bars
Thermal	Glass Transition temperature (ASTM D3418)	150	°C
Test Method	Flexural Modulus (E) (ASTM D790)	8(Nominal)	GPa
	Flexural Strength (ASTM D790)	120(Nominal)	MPa

Based on our best knowledge, this document is believed to be reliable information. However, these results will be vary from lab to lab, and will be dependent on molding techniques, sample preparation and testing methods. Because of variations in the methods, condition and equipment used commercially in processing this product, no warranties and guarantees are made as to be suitability of products for the applications disclosed. We recommend that each application be evaluated to assess the suitability of the product to meet specific requirements. CPL does not assume any liability that may result from the use of the document.